



1260 MG-KRETE™ NO ODOR By Imco®

DESCRIPTION

1260 MG-KRETE™ NO ODOR is an inexpensive, two component, high early strength structural repair material that is very easy to use in the field.

BASIC USES

1260 MG-KRETE™ NO ODOR is used for all types of concrete repairs. It is used for patching, from shallow feathering to deep pours. It can be poured into forms, it can be trowelled vertically and overhead, it can fill large cracks or be used as a fast set plug. It can be used as overlay material.

MAJOR ADVANTAGES OF 1260 MG-KRETE™ NO ODOR

- Cures very rapidly in above 40° F (4.4°C) temperatures to form a very hard, tenaciously bonded repair
- Non-flammable and has high heat resistance.
- Cures very rapidly, most applications can be returned to service in 1 hour.
- Does not shrink on cure.
- Stronger than concrete within 45 minutes.
- Self-priming and will bond to virtually any construction material.
- Very easy to use, there are no specific slump requirements, no critical mixing ratios, no sophisticated and expensive surface preparation.
- Non-toxic, it contains no harmful chemicals, and it cleans-up with water.
- Very cost effective, it has the performance characteristics of the best polymers at a fraction of the cost.
- Totally waterproof, it is resistant to oils, gasoline, salt and UV radiation.
- Approved by Agriculture Canada for incidental food contact.

TECHNICAL AND PRODUCT DATA

- Flash Point: none
- Compressive Strength:

45 minutes	1,500 psi / 10.3 MPa
24 hours	2,600 psi / 17.9 MPa
7 days	3,800 psi / 26.2 MPa
28 days	7,800 psi / 53.8 MPa
- Set Time:

-Initial At 20°C (68°F)	25 minutes
-------------------------	------------
- Application temp.:

minimum – 4.4°C (40°F) (with Low Temp. Accelerator)	
over 40°C (100°F) (with High Temp. Retarder)	
- Primer: No primer required
- Clean-up: Water (before material sets)
- Shelf Life: 1 year, if stored away from direct heat
- No. of Components: Two (Part A and B)
- Available in fine or regular grade
- Packaging:

Regular grade	22.7 kg (50lb) Part A with 3.78L (1gal) Part B
Fine grade	20.0 kg (45lb) Part A with 3.78L (1gal) Part B
- Also available in bulk packaging.
- Yield :

Regular grade:	1 unit = 0.45 cu. ft. of mixed material
	78 units = 1 cu. meter
Fine grade:	1 unit = 0.40 cu. ft. of mixed material

Both grades can be increased by adding clean dry aggregates during mixing.

**Do not use limestone with 1260 MG-KRETE™ NO ODOR
FOR INDOOR USE INCLUDING RESIDENTIAL
*****DO NOT FREEZE PART B*******

1260 MG-KRETE™ NO ODOR

MIXING

Keep all materials dry, **DO NOT ADD WATER TO THE MIX**. Maintaining the mix ratio as supplied, i.e. one container of liquid activator to one bag of dry component, will give a trowellable consistency suitable for most floor applications, however the slump may be adjusted to the applicator's preference or to suit the specific job conditions by increasing either of the two components. **DO NOT ADJUST THE SLUMP BY THE ADDITION OF WATER**. Mix the two components by mechanical means until all the material is wetted,. Let slake for at least 1 minute and remix, remove from container and place quickly. Dry pea gravel may be added to the mix to increase the yield on deep placements.

APPLICATION INSTRUCTIONS

Surface must be clean, dry and free of loose material. Remove all dirt from area to be covered leaving a rough, clean surface. For applications at ambient temperatures below 50°F (10°C) 1261 LOW TEMP ACCELERATOR must be used to ensure a full cure. With temperatures above 68°F (20°C) the 1263 HIGH TEMPERATURE RETARDER can be used to extend the working time. Do not pre-wet surface. Keep an adequate supply of water on hand to keep equipment clean. Thoroughly dry all equipment before using **1260 MG-KRETE™ NO ODOR**.
*******DO NOT FREEZE PART B.**

FINISHING

1260 MG-KRETE™ NO ODOR may be finished with screed, trowel or broom. Do not rework material after it has begun to set.

OVER COATING - Allow **1260 MG-KRETE™ NO ODOR** at least 24 hours to cure before over coating. The cured surface should be sandblasted or mechanically abraded before coating to ensure sound bonding.

SPECIAL HANDLING

Store materials in a clean dry area away from direct heat. Setting time of the mixed material will be greatly accelerated if the components are stored in a warm or hot environment, conversely, the setting time is extended if the materials are kept cool. Flush all spills with water. Clean all tools with water immediately after each use. Do not attempt to place **1260 MG-KRETE™ NO ODOR** in water or where running water will disturb the worksite.
*******DO NOT FREEZE PART B.**

SAFETY

Please refer to SDS at www.imcotechnologies.com. Use the same precautions as when working with conventional concrete. Although the materials are non-toxic it is good practice to protect exposed skin areas and to wear a face mask to prevent inhalation of the aggregate particles. A small amount of ammonia gas is released during the cure, venting of indoor areas may be required in some applications, although this will present no problems outdoors. Neither of the components nor the mixed product are flammable.

WARRANTY DISCLAIMER

The information herein is to assist customers in determining whether our products are suitable for their application. Our products are intended for sale to industrial and commercial customers. We request that customers inspect and test our products before use and satisfy themselves as to the contents and suitability. We warrant that our products will meet our written specifications. Nothing herein shall constitute a warranty expressed or implied, including any warranty of merchantability or fitness, nor is protection from any loss or patent to be inferred. The exclusive remedy for all proven claims is replacement of our materials and in no event shall we be liable for special, incidental or consequential damages.

IMCO TECHNOLOGIES
6254 SKYWAY RD., PO BOX 915
SMITHVILLE, ON. L0R 2A0

TEL 1-877-957-4626
FAX 905-527-0606

info@imcotechnologies.com
www.imcotechnologies.com

IMCO TECHNOLOGIES
3909 Witmer RD, Suite 1014
NIAGARA FALLS, NY 14305